



SAQ  
SIAT

**TECHNICAL SPECIFICATION  
GMAW WELDING WIRE  
PITTARC G3Ni1**

Document  
Revision  
Date  
Page

SPP173  
00 i  
30.01.15  
1/2

**1. DESCRIPTION**

Gas shielded welding wire conforming to the standard UNI EN ISO 14341-A- G 50 4 M21 3Ni1 and AWS A5.28 ER80S-Ni1 suitable to join Ni low alloy steels for low temperature applications. Available in copper coated wire and *no-copper* wire.

**2. PRODUCT CHEMICAL COMPOSITION (%)**

		C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Al	V	Ti+Zr
PITTARC G3Ni1	Min	0.07	1.00	0.60	-	-	-	0.80	-	-	-	-	-
	Max	0.12	1.20	0.80	0.020	0.020	0.15	1.00	0.15	0.20	0.02	0.03	0.15
EN ISO 14341-A G3Ni1	Min	0.06	1.00	0.50	-	-	-	0.80	-	-	-	-	-
	Max	0.14	1.60	0.90	0.020	0.020	0.15	1.50	0.15	0.35	0.02	0.03	0.15
AWS A5.28 ER80S-Ni1	Min	-	-	0.40	-	-	-	0.80	-	-	-	-	-
	Max	0.12	1.25	0.80	0.025	0.025	0.15	1.10	0.35	0.35	-	0.05	-

**3. WIRE DIMENSIONS**

Standard diameter (mm) : 0.8 ; 1.0 ; 1.2 ; 1.4 ; 1.6  
Permissible deviations : ISO 544

**4. CAST AND HELIX (STANDARD PACKAGING)**

Cast (mm) : 800 ÷ 1000  
Helix (mm) : maximum 10

**5. ALL-WELD-METAL MECHANICAL PROPERTIES**

	Re MPa	Rm MPa	A5 %	KV (-40°C) J
AWS A5.28 ER80S-Ni1	≥ 470	≥ 550	≥ 24	27
EN ISO 14341-A- G 50 4 M21 3Ni1	≥ 500	560 ÷ 720	≥ 18	≥ 47

**Gas protection** : ISO 14175 M21 mixture . Interpass temperature max 250°C


**Recommended welding parameters (diam. 1,2 mm):** 260÷300A; 25÷30V; wire feed speed ~5m/min; travel speed ~6mm/sec; tip to work ~20mm.

**6. STANDARD PACKAGING.**

Wire basket rim RG (ISO 544 B300) of 18 kg net weight. Each spool sealed in a polyethylene airtight bag and packed into a cardboard box. 72 spools stacked onto a pallet secured by thermoplastic shrink-wrapping (94x125x80 cm, 1296kg net weight). Available cardboard drums of about 250kg net weight, each one stacked onto a pallet 105x105x90 cm of about 1000kg total weight, secured by thermoplastic shrink-wrapping. On request packaging available from 15 kg up to 700 kg.

**7. STANDARD IDENTIFICATION.**

A label is attached to the inside of each spool containing nominal diameter, trade name, classification, heat number, operator code. A label is attached to every box containing manufacturer, trade name, nominal diameter, heat number, spool type, references to the standards, and approvals.






SAQ  
SIAT

TECHNICAL SPECIFICATION  
GMAW WELDING WIRE  
PITTARC G3Ni1

Document  
Revision  
Date  
Page

SPP173  
00 i  
30.01.15  
2/2


	SIAT S.p.A. 33013 Gemona del Friuli (UD) ITALY		
<b>PITTARC G3Ni1</b>			
Welding wire for carbon steels and fine grained steels EN ISO 14341-A – G 50 4 M21 3Ni1 and AWS A5.28 ER80S-Ni1			
Shielding gas according to ISO 14175 M21 Current/Polarity G+, Welding positions: PA, PB, PC, PF			
Weight kg	Heat N°	Diameter	Spool type
XX	XXXXX/XX	X,X mm	X XXX

## 8. STANDARD CERTIFICATION.

Documents according to EN 10204

## 9. APPROVALS

None



SIAT – Società Italiana  
Acciai Trafilati S.p.A.  
Via Facini, 54  
33013 Gemona del Friuli  
(Ud)  
Tel.: +39 0432 062911  
Fax: +39 0432  
[www.pittini.it](http://www.pittini.it)

All data/information of this document are only at informative title and not binding for SIAT S.p.A., who entitles full right to modify/change them without prior notice.